

44A Contact adhesive

Revision: 16/07/2019

Page 1 from 1

Technical data

Basis	Polychloroprene rubber (neoprene).
Consistency	Fluid
Curing system	Physical drying and crystallisation
Density	Ca. 0,86 g/ml
Open time (*)	Ca. 10 min.
Consumption (*)	Ca. 300 ml/m ² , each side
Temperature resistance**	-20 °C → 70 °C
Application temperature	5 °C → 25 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

44A Contact adhesive is a universal, toluene free, solvented ready to use contact adhesive based upon rubber and synthetic resins.

Properties

- Fast drying
- High adhesive strength
- Moisture resistant.

Applications

- Bonding of many materials such as rubber, leather, cork, plastic, felt, etc. on various types of substrates or among themselves.
- Bonding synthetic decoration panels and worktops in wood, metal or board.

Packaging

Colour: yellow

Packaging: tube 50ml, tube 125ml, metal tin 750ml, metal tin 5L

Shelf life

24 months unopened and stored in dry and cool conditions (Between 5 and 25 °C)

Substrates

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: No pretreatment required.

44A Contact adhesive can be applied on all substrates, except for PS (polystyrene), PE, PP, PTFE. We recommend a preliminary adhesion test on any substrate.

Application method

Apply the adhesive uniformly with a notched trowel or a brush on both sides of the surfaces that need to be glued. Wait ca. 10 minutes and join both parts together. Afterwards push firmly.

Cleaning: With Adhesive Cleaner 90A.

Repair: With the same material.

Health- and Safety Recommendations

Take the usual labour hygiene into account. Use only in well-ventilated areas. Do not smoke. In case of insufficient ventilation it is appropriate to wear respiratory protection. Consult label and material safety data sheet for more information.

Remarks

- The applied pressure and not the duration of the compression will determine the ultimate strength of the bond.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.