

level fast

Fast-setting high performance leveller with FST

DESCRIPTION

Fast-setting, high performance single part polymer-modified, protein-free, fibre cementitious leveller for floors.

Use for

- Fast laying on absorbent and non-absorbent internal substrates; to prepare most floor surfaces including timber floors prior to installing:
 - Ceramic & porcelain tiles.
 - Glass/ceramic/stone mosaic tiles.
 - Natural stone.
 - Wooden flooring (Inc. parquet flooring, laminates)
- NOTE:* BAL LEVEL FAST is not suitable as a wearing surface
- Bed depth from 2mm up to 30mm thickness in a single application.
- Internal applications
- Dry environments only, unless using BAL WATERPROOFING KIT FOR SHOWERS, BAL WP1 TANKING SYSTEM or BAL TANK-IT.
- Suitable for underfloor heating.
- Domestic or commercial use (NOTE: for large areas we would recommend BAL LEVEL MAX.

USAGE: Bed Thickness / Time

| Bed Thickness | Pot Life | Setting Time [^] |
|---------------|--------------|---------------------------|
| 2mm – 30mm* | 10 - 15 mins | 30 minutes at 20°C |

. ^ Can receive ceramic or natural stone tiles after 45 minutes at 20°C. Allow a minimum of 24 hours for wood flooring and painting.

*Up to 30mm in a single application.

Note: Ensure direct to earth subfloors incorporate an affective damp proof membrane.

TEMPERATURE RESISTANCE***

-30°C to 100°C

*** Cured leveller.

Restrictions: NOT suitable for

- Exterior use or total immersion areas (e.g. swimming pools).

PRODUCT INFORMATION

Composition: Single-part, fibre reinforced, polymer modified rapid setting and shrinkage compensated cement-based levelling compound. The formulation is protein-free.

Colour: Grey.

Type/Classification: Exceeds BS EN 13813 CT – C30 – F7 – Cementitious screed, Compressive Strength is >30N/mm² and Flexural Strength is >7N/mm² after 28 days

Pack sizes: 20kg

Key Features:

- Bed depth 2mm – 30mm*
- Fibre Strand Technology (FST) for improved flexibility and resilience.
- Suitable for timber floors (minimum thickness 3mm)
- Accepts foot traffic in 30 minutes at 20°C
- Self-smoothing, shrinkage compensated with 'one pour' excellent flow.
- Protein free formulation
- Excellent coverage: 4m² at 3mm thickness

Tile After: 45 minutes (at 20°C)

TOOLS/COVERAGE

| Recommended Application Tool | Typical Coverage ^{^^} at 3mm bed-thickness |
|------------------------------|---|
| Steel trowel | 0.2m ² /kg |

^{^^} May vary dependent on nature and flatness of surface, and thickness of application.

SURFACE PREPARATION

General

Ensure surfaces are dry, sound, and free from grease, dust and any other contamination/barriers to adhesion.

All primed areas should be fully dry.

Ensure direct-to-earth sub-floors incorporate an effective damp proof membrane.

Surface regularity:

Surface Regularity is defined as the deviation in height of the surface of a flooring layer over short distances in a local area. In simpler terms, it is the 'flatness' or 'measure of unevenness' of the screeded surface.

| Class | MAXIMUM PERMISSABLE DEVIATION - 2M STRAIGHT EDGE (MM) | APPLICATION |
|-------|---|---|
| SR1 | 3mm | Recommended for direct fixing of tiles and slabs with a tile adhesive |

In wet areas: Allow a minimum of 24 hours before waterproofing BAL LEVEL FAST with BAL WATERPROOF 1C or BAL TANK-IT.

SUITABLE SURFACES include:

Asphalt (suitable grade e.g. flooring)

Must be of a suitable grade, be clean, in sound condition (without brittleness, softening. etc.) and have adequate cohesive strength, a natural float finish and laid on a firm rigid base.

Clean thoroughly to remove surface dirt using warm water and a suitable detergent. Remove all detergent residues with clean water. No priming is needed.

Ensure that surface is sufficiently regular to suit bedding depths of BAL LEVEL FAST.

Apply leveller as required, minimum 3mm to maximum 6mm.

Concrete; cement:sand screeds

Must be fully cured and free from efflorescence, laitance, dirt, polished concrete and other loose materials. Remove by the use of suitable mechanical methods.

Allow the following minimum drying times:

- Concrete: 6 weeks
- Cement:sand screed: 3 weeks

Absorbent cement:sand screeds and concrete.

Prime with BAL PRIME APD pre-diluted 1:1 with clean water.

Allow to dry.

Low-absorbent cement:sand and concrete.

Dampen with clean water before laying BAL LEVEL FAST.

Ceramic tile adhesive residues

Remove as much adhesive as possible.

Ensure all residual adhesive is soundly bonded.

No priming is needed.

Do not apply over old adhesive residues that are softened by water.

BACKGROUNDS / BASES

BACKGROUNDS / BASES

| | |
|---|---|
| Cement:Sand Screeds and Concrete with low/highly absorbent surface (2)(7) | ✓ |
| Cement:Sand Screeds with Underfloor Heating (2)(3) | ✓ |
| Overlaid Timber Floors (3)(4) | ✓ |
| T&G Floorboards (8) | ✓ |
| Single Layer Plywood (4)(8) | ✓ |
| Ceramic tile adhesive residues | ✓ |
| Unglazed Ceramic Tiles / Hard Natural Stone | ✓ |
| Tile Backer/Fibre Cement Boards (2)(3) | ✓ |
| Mastic Asphalt (6) | ✓ |
| Anhydrite/Calcium Sulfate Screeds (3)(5) | ✓ |

USAGE & SERVICE CONDITIONS

| | | | |
|-----------------------------------|---|----------------------------|---|
| Walls | ✗ | Floor | ✓ |
| Interior | ✓ | External | ✗ |
| Dry | ✓ | Wet Areas (1) | ✓ |
| Worktops (1) | ✓ | Showers (1) | ✓ |
| Swimming Pools | ✗ | Domestic/ Commercial | ✓ |
| Underfloor Heating Systems (2)(3) | ✓ | Limited Movement/Vibration | ✓ |

(1) In wet conditions tank out with BAL WATERPROOF 1C or BAL TANK-IT.

(2) Where the surface is high absorbency, prime with BAL PRIME APD 1:1 with water).

(3) Check suitability for the intended purpose with the manufacturer.

(4) Seal back face and edges with undiluted BAL BOND SBR.

(5) Prime with BAL PRIME APD, first coat 1:1 with water, second coat undiluted 90° to the first.

(6) Check suitability of the grade of asphalt (flooring grade only).

(7) Where the surface has low absorbency, dampen with clean water.

(8) Prime with undiluted BAL PRIME APD.

Cement:sand screeds with underfloor heating

Switch off heating for MINIMUM 48 hours before application of BAL LEVEL FAST. Follow accordance with manufacturer's instructions.

Prime floor surface with BAL PRIME APD pre-diluted 1:1 with clean water.

NOTE: For further information on other backgrounds and preparation, contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.

Anhydrite/calcium sulfate and hemi-hydrate screed

Allow the screed to dry out in accordance with manufacturer's instruction example: moisture contact below 0.5% w/w or 75% RH (Relative Humidity). Mechanically remove top surface to remove weak/dusty surface layer(s) as per the screed manufacturer's recommendations. Remove all dust and loose material e.g. by vacuum etc. before priming with 2 coats of (second coat applied at 90° to the first):

– BAL PRIME APD diluted 1:1 with clean water and second coat undiluted or

– BAL BOND SBR diluted 1:4 with clean water and second coat diluted 1:2 with clean water.

Allow each coat of primer to dry.

NOTE: For further information on other backgrounds and preparation, contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.

Fibre reinforced cement boards and lightweight tile backer boards

Install boards to BS 5385 – i.e. moisture-resistant boards screwed to seasoned timber or suitable proprietary framework at maximum 300mm centres or as per the board manufacturer's recommendations. Ensure no fixings protrude.

Some boards may require priming, prior to tiling with a cementitious based tile adhesive. Use a suitable primer from the BAL range. Please refer to the relevant BAL TECHNICAL DATA SHEETS for further information.

IMPORTANT NOTE: Obtain manufacturer's confirmation that boards are suitable for tiling and for relevant fixing instructions. For further information on other backgrounds and preparation, contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.

Existing vinyl tiles

Ensure these are in good sound condition and securely bonded to their base.

Remove loose or damaged tiles/areas of sheet along with any loose or soft adhesive.

Remove any polishes, wax, grease etc. with a suitable proprietary cleaner.

Prime Surface with undiluted BAL BOND SBR and allow to dry. Level within 24 hours of application.

Timber floors (hard floor finishes)

Overlaid timber floors (min. 15mm)

Ensure timber floor (i) is sufficiently rigid and stable to receive tiles; (ii) can carry the additional static and dynamic load without excessive deflection; and (iii) has adequate ventilation under the timber.

Overlay existing timber floor with a suitable water resistant, marine plywood, min. 15mm thick, screwed (not nailed) at 300mm centres.

Seal timber surface on the underside and edges with undiluted BAL BOND SBR. Allow to dry.

Prime board surface with 2 coats of undiluted BAL PRIME APD, applying second coat at 90° to the first.

Allow each coat to dry.

Tongued and grooved floorboards/18mm single layer WBP plywood

Ensure boards are dry, rigid and securely fixed (screwed to joints at 300mm centres, including any cross-noggings, if necessary). Sand (abrade) surface and ensure any surface coatings removed, e.g. varnish, lacquers, etc.

Before priming with 2 coats of (second coat applied at 90° to the first):

– BAL PRIME APD (undiluted) or

– BAL BOND SBR (diluted 1:2 by volume with clean water)

Allow each coat of primer to dry.

NOTE: For further information on other backgrounds and preparation contact BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE.

Uneven timber floors (for soft floor finishes inc. vinyl, linoleum, carpet).

Ensure boards are (i) dry, rigid and securely fixed; (ii) has adequate ventilation under the timber.

Lay BAL LEVEL FAST and allow to dry for a minimum of 24 hours before soft finished can be installed.

If required screw down layer of a suitable 12mm plywood compliant with BS6566 onto this levelled base.

MIXING

Use a BAL MIXING BUCKET or other suitable bucket.

1. Add approximately 5 parts powder to 1 part clean cold water by weight. (see table below)
2. Mix until lump-free mortar achieved.
3. Allow mixed leveller to stand for 2 minutes before re-mixing for 30 seconds.

| Product Size | Usage | Approx., clean cold water required per size |
|--------------|--------|---|
| 20kg | Floors | 4.20 litres |

NOTE: *If using electric drill mixer*, blend at slow speed (i.e. under 300rpm).

Ready for immediate use. Pot life at 20°C: approx. 10-15 minutes.

NOTE: Pot life/setting time will vary slightly with temperature: higher temperatures = shorter; lower temperatures = longer.

APPLICATION/USAGE

Do NOT use in temperatures below 5°C or in damp conditions.

Trowel recommendations

| Area | Recommended Application Tool |
|----------------------------|------------------------------|
| Small /medium size floors. | Steel trowel |

Usage procedure

1. Prime the floor surface if required and allow to dry before mixing BAL LEVEL FAST. Note: Timber board joints where gaps between boards are open, use thin heavy duty tape to bridge joints, care must be taken not to over everywhere in tape (this will help to minimise the leveller disappearing beneath the sub-floor).
2. Pour mix over sub-floor and spread to required depth using a suitable steel finishing trowel or long hand blade.
3. Surface should be sufficiently smooth to receive floor coverings without further treatment. Note: Do NOT use a spiked roller; this will pull the fibres to the surface.

If any trowel marks remain rub down before compound has hardened (within 20 - 30 minutes at 20°C).

4. Allow new floor surface to set. Depending on thickness of application, a 3mm layer BAL LEVEL FAST can receive foot traffic after 30 minutes and receive tiling after 45 minutes.
5. Show existing movement joints within the sub-floor and BAL LEVEL FAST when receive tile finishes.
6. Allow BAL LEVEL FAST to set for 24 hours when receive floor finishes such as wooden flooring.

HEALTH & SAFETY INFORMATION / GOOD PRACTICE ADVICE

For detailed information and safety guidance, please refer to Product Material Safety Data Sheet [MSDS].

TECHNICAL ADVISORY SERVICE

For free expert guidance on use of this product, or any aspect of tiling, contact the BAL TECHNICAL ADVISORY AND SPECIFICATION SERVICE on Tel: 01782 591120 or 03330 030160 or Email: info@building-adhesives.com

SHELF LIFE

12 months under normal dry conditions. Protect from frost and damp.

QUALITY AND ENVIRONMENTAL STANDARDS

Manufacturing quality assurance standards conform to BS EN ISO 9001. Satisfies the environmental management requirements and operational scope of ISO 14001.

25 YEAR GUARANTEE

All BAL products are supplied with a 25-year product guarantee to be free from manufacturing defects and to be fit for purpose. The guarantee covers materials replacement costs and labour. This guarantee is subject to use of product in accordance with BAL's instructions and technical data, and good working practice. No liability can be accepted for any loss or damage arising from incorrect use of products or poor workmanship, over which BAL has no control. While products may be suitable for installations internally or externally, products when used externally are exempt from cover under the BAL 25 Year Guarantee. Terms and conditions apply. Full details are available for your review at www.bal-adhesives.com.

CONDITIONS OF SALE

Sold subject to the Company's Conditions of Sale. Available on request.

For sales and technical queries, contact:

BUILDING ADHESIVES LTD

Longton Road, Trentham, Stoke-on-Trent, ST4 8JB, England
www.bal-adhesives.com

Sales

Tel: +44 (0) 1782 591160

Fax: +44 (0) 1782 591131

Technical

Tel: +44 (0) 1782 591120 or

+44 (0) 3330 030160

Email: info@building-adhesives.com

Ireland

Unit 622, Phase III

Northwest Business Park

Ballycoolin, Dublin 15, Ireland

Tel: +353 (0) 1 880 9210

Fax: +353 (0) 1 880 9211

NOTE: BAL reserves the right to update instructions, technical data and other information at any time without notice.

PorcelBond Plus™ is a trademark of Building Adhesives Ltd

